



AZAR SHAHAB REFRACTORIES CO.

ARB-AI75

General Properties

Raw Material Basis..... Bauxite

Main Chemical Component

Al ₂ O ₃ (%)	SiO ₂ (%)	Fe ₂ O ₃ (%)
Max 75	Min 19	Min 2

Physical & Thermal Properties

Reversible Thermal Expansion at 1000 °C (%)	0.70-0.80
Bulk Density (gr/cm ³)	2.45-2.55
Apparent Porosity (%)	17-22
Cold Crushing Strength (kg/cm ²)	450-650
Refractoriness (°C)	1820
Refractoriness Under Load (°C)	1400-1420
Thermal Shock at 1000 °C (cycle)	25-35

All data subject to reasonable deviation and therefore, should not be used for specification purposes.

Phone : 041 – 33467521-7

Fax : 041 – 33467247

Web: www.azarshahab.com

Email: info@azarshahab.com