



AZAR SHAHAB REFRACTORIES CO.

ARCAST LW A40

General Properties

Classification	Insulating Castable
Description	Light Weight Hydraulic Bonded Refractory Castable
Raw Material Basis	Light Weight Fireclay
Bond	Hydraulic
Installing Method	Casting / Vibrating
Packaging	25 kg net weight multi proof sacks
Storage Life (Month)	9
Grain Size (mm)	Max 5
Water Required (%)	30-40

Main Chemical Component

Al ₂ O ₃ (%)	SiO ₂ (%)	Fe ₂ O ₃ (%)	CaO (%)
42	44	1.5	11

Physical & Thermal Properties

Maximum Service Temperature (°C)	1350
Bulk Density at 1000°C (gr/cm³)	1.30-1.50
Cold Crushing Strength (kg/cm²)	
After Drying at 110 °C	70-100
After Firing at 1000 °C.....	60-80
Permanent Linear Change (%)	
After Drying at 110 °C	(-0.3) to (-0.1)
After Firing at 1000 °C	(-0.6) to (-0.4)
Thermal Conductivity (w/m^{°K}) at 800 °C	0.25

All data subject to reasonable deviation and therefore, should not be used for specification purposes.

Phone : 041 – 33467521-7

Fax : 041 – 33467247

Web: www.azarshahab.com

Email: info@azarshahab.com