



## AZAR SHAHAB REFRACTORIES CO.

### ARCAST LW A40I

#### General Properties

<b>Classification</b> .....	Insulating Castable
<b>Description</b> .....	Light Weight Hydraulic Bonded Refractory Castable
<b>Raw Material Basis</b> .....	Light Weight Fireclay
<b>Bond</b> .....	Hydraulic
<b>Installing Method</b> .....	Casting / Vibrating
<b>Packaging</b> .....	25 kg net weight multi proof sacks
<b>Storage Life (Month)</b> .....	9
<b>Grain Size (mm)</b> .....	Max 5
<b>Water Required (%)</b> .....	30-40

#### Main Chemical Component

Al <sub>2</sub> O <sub>3</sub> (%)	SiO <sub>2</sub> (%)	Fe <sub>2</sub> O <sub>3</sub> (%)	CaO (%)
38	41	6	12

#### Physical & Thermal Properties

<b>Maximum Service Temperature (°C)</b> .....	1350
<b>Bulk Density at 1000°C (gr/cm<sup>3</sup>)</b> .....	1.20-1.40
<b>Cold Crushing Strength (kg/cm<sup>2</sup>)</b>	
After Drying at 110 °C .....	50-100
After Firing at 1000 °C.....	40-80
<b>Permanent Linear Change (%)</b>	
After Drying at 110 °C .....	(-0.3) to (-0.1)
After Firing at 1000 °C .....	(-0.6) to (-0.4)
<b>Thermal Conductivity (w/m<sup>°K</sup>) at 800 °C</b> .....	0.25

All data subject to reasonable deviation and therefore, should not be used for specification purposes.

**Phone : 041 – 33467521-7**

**Fax : 041 – 33467247**

**Web: [www.azarshahab.com](http://www.azarshahab.com)**

**Email: [info@azarshahab.com](mailto:info@azarshahab.com)**