



AZAR SHAHAB REFRACTORIES CO.

ARCAST 30ADSiC60LCC

(Special Andalusite-SiC Low Cement Castable for Cement and Steel Industry)

General Properties

Classification	Alumina Castable
Description	Low Cement Hydraulic Bonded Refractory Castable
Raw Material Basis	Andalusite/SiC
Bond	Hydraulic
Installing Method	Casting / Vibrating
Packaging	25 kg net weight multi proof sacks
Storage Life (Month)	9
Grain Size (mm)	Max 6
Water Required (%)	5.5-6.5

Main Chemical Component

Al ₂ O ₃ (%)	SiO ₂ (%)	Fe ₂ O ₃ (%)	CaO (%)	SiC (%)
25	12	0.5	2	60

Physical & Thermal Properties

Maximum Service Temperature (°C)	1600
Bulk Density at 110 °C (gr/cm³)	2.55-2.75
Cold Crushing Strength (kg/cm²)	
After Drying at 110 °C	700-900
After Firing at 1450 °C.....	750-950
Permanent Linear Change (%)	
After Drying at 110 °C	Negligible
After Firing at 1000 °C	(-0.2) to (+0.2)

All data subject to reasonable deviation and therefore, should not be used for specification purposes.

Phone : 041 – 33467521-7

Fax : 041 – 33467247

Web: www.azarshahab.com

Email: info@azarshahab.com