



AZAR SHAHAB REFRACTORIES CO.

ARCAST A60

General Properties

Classification	Alumina Castable
Description	Classical Hydraulic Bonded Refractory Castable
Raw Material Basis	Bauxite
Bond	Hydraulic
Installing Method	Casting / Vibrating
Packaging	25 kg net weight multi proof sacks
Storage Life (Month)	9
Grain Size (mm)	Max 6
Water Required (%)	10-12

Main Chemical Component

Al ₂ O ₃)%	SiO ₂)%	Fe ₂ O ₃)%	CaO)%
60	28	1.6	4

Physical & Thermal Properties

Maximum Service Temperature (°C)	1540
Bulk Density at 110 °C (gr/cm³)	2.25-2.35
Cold Crushing Strength (kg/cm²)	
After Drying at 110 °C	600-800
After Firing at 1350 °C.....	500-700
Permanent Linear Change (%)	
After Drying at 110 °C	Negligible
After Firing at 1000 °C	(-0.4) to (+0.2)

All data subject to reasonable deviation and therefore, should not be used for specification purposes.

Phone : 041 - 33467521-7

Fax : 041 - 33467247

Web: www.azarshahab.com

Email: info@azarshahab.com