



AZAR SHAHAB REFRACTORIES CO. ARCAST A97MCC

General Properties

Classification	High Alumina Castable
Description	Medium Cement Hydraulic Bonded Refractory Castable
Raw Material Basis	Tabular Alumina
Bond	Hydraulic
Installing Method	Casting / Vibrating
Packaging	25 kg net weight multi proof sacks
Storage Life (Month)	9
Grain Size (mm)	Max 6
Water Required (%)	6.0-8.0

Main Chemical Component

Al ₂ O ₃ (%)	SiO ₂ (%)	Fe ₂ O ₃ (%)	CaO (%)
97	0.1	0.1	2.8

Physical & Thermal Properties

Maximum Service Temperature (°C)	1860
Bulk Density at 110 °C (gr/cm³)	2.85-3.05
Cold Crushing Strength (kg/cm²)	
After Drying at 110 °C	700-900
After Firing at 1400 °C.....	750-950
Permanent Linear Change (%)	
After Drying at 110 °C	Negligible
After Firing at 1000 °C	(-0.2) to (+0.2)

All data subject to reasonable deviation and therefore, should not be used for specification purposes.

Phone : 041 – 33467521-7

Fax : 041 – 33467247

Web: www.azarshahab.com

Email: info@azarshahab.com